CUSTOMER: **PRECIX**

LAB RPT. #: **112165** DATE: 3/2/2009

SPEC./DWG #: Bio Diesel REV.: NA

PART #: NA APCO: NA

COMPOUND: 13718 (F74) LOT # 8106

PRECIX, INC. - TEST REPORT

TYPE OF TEST	TEST METHOD	SPEC.	ACTUAL	PASS Y/N	TYPE OF TEST	TEST METHOD	SPEC.	ACTUAL	PASS Y/N
ORIGINAL PROPERTIES					**FLUID AGING PROPERTIES**				
Durometer, Shore A, pts	D-2240	65 to 75	70	Y	**B5 Rapeseed**				
Tensile Strength, MPa, min.	D-412	10	12.8	Y	70hrs. at 23°C				
Elongation Strength, %, min.	D-412	200	251	Y	Duro Change, Shore A, pts	D-471	Report	0	NA
					Tensile Change, %		Report	+1.1	NA
FLUID AGING PROPERTIES					Elongation Change, %		Report	+12.1	NA
B20 Rapeseed					Volume Change, %		Report	-0.1	NA
70hrs. at 23°C									
Duro Change, Shore A, pts	D-471	Report	0	NA	**FLUID AGING PROPERTIES**				
Tensile Change, %		Report	-2.2	NA	**B5 Soybean**				
Elongation Change, %		Report	+6.4	NA	70hrs. at 23°C				
Volume Change, %		Report	+0.1	NA	Duro Change, Shore A, pts	D-471	Report	-2	NA
					Tensile Change, %		Report	+27.9	NA
FLUID AGING PROPERTIES					Elongation Change, %		Report	-4	NA
B20 Soybean					Volume Change, %		Report	-2	NA
70hrs. at 23°C									
Duro Change, Shore A, pts	D-471	Report	-1	NA					
Tensile Change, %		Report	+0.9	NA					
Elongation Change, %		Report	+6	NA					
Volume Change, %		Report	+0.1	NA					

Notes/Comments: **Post Cure 24 @ 482**

DPRF 1536-09

Any changes/updates to the lab report will be denoted by a double asterisk, (**), along with an updated report/signature date.

This report shall not be reproduced except in full, without the written consent of the Precix, Inc. Laboratory Manager.

This report shall not be reproduced except in full, without the written consent of the Precix Laboratory Manager.

BY AUTHORIZED AGENT: Scott Bourgeois, Materials Engineer, 3/2/09
(Name, Title, Date)

APPROVAL TO SUBMIT FOR PPAP: Scott Bourgeois, Materials Engineer, 3/2/09
(Name, Title, Date)

Precix - 744 Belleville Avenue - New Bedford, MA 02742
TEL: (508) 998-4000 FAX: (508) 998-4100