

CUSTOMER: **Precix**LAB RPT. #: **111210**DATE: **20.11.2006**SPEC./DWG #: **Various % of Fuel C & Ethanol**REV.: **N/A**PART #: **N/A**APCO: **N/A**COMPOUND: **13705OM (F05)**LOT #: **N/A****PRECIX, INC. - TEST REPORT**

TYPE OF TEST	TEST METHOD	SPEC.	ACTUAL	PASS Y/N	TYPE OF TEST	TEST METHOD	SPEC.	ACTUAL	PASS Y/N
13705 (F05)									
Fluid Aging Properties									
85% Ethanol / 15% Fuel C									
1000 hrs. at 60°C									
Duro Change, Shore A, pts	D-471	Report	-17						
Tensile Change, %, Max.		Report	-53						
Elongation Change, %, Max.		Report	-18						
Volume Change, %		Report	+21						
13705 (F05)									
Fluid Aging Properties									
100% Ethanol									
1000 hrs. at 60°C									
Duro Change, Shore A, pts	D-471	Report	-13						
Tensile Change, %, Max.		Report	-44						
Elongation Change, %, Max.		Report	-6						
Volume Change, %		Report	+15						
Original Properties									
Durometer, Shore A, pts.	D-2240	Report	73						
Tensile Strength, Mpa, min.	D-412	Report	1642						
Elongation, %, min.		Report	344						
S.G.	D-297	Report	2.19						

NOTES/COMMENTS:

Any changes/updates to the lab report will be denoted by a double asterisk, (**), along with an updated report/signature date.

This report shall not be reproduced except in full, without the written consent of the Precix, Inc. Laboratory Manager.

 BY AUTHORIZED AGENT: Ryan Furno Lab Manager 11/20/06
 (Name, Title, Date)

 APPROVAL TO SUBMIT FOR PPAP: Ryan Furno Lab Manager 11/20/06
 (Name, Title, Date)

 Precix, Inc. - 744 Belleville Avenue - New Bedford, MA 02742
 TEL: (508) 998-4000 FAX: (508) 998-4100